



LYNEL SG

Composition

- 95 gsm latex paper
- PVC Plastisol
- Viscose 0.9dtex ground flock

Technical information

- Total grammage (Int CRT03/006) : 245 g/m²
- Average thickness (Int CRT03/010) : 0.45mm
- Residual PH (DIN 53124) : ≥ 8
- Light fastness (blue scale) : 4 to 7 according to the shade (example: hermine =7)
- Wet bleeding resistance (gray scale) : 3 to 5 according to the shade (example Baribald = 5)

Roll packaging

Roll size : 100 linear meters x104cm width
Enrolled on 76mm inside core.
Cardboard box of 32 x 32 x 112 cm
Weight : 28 kg

Best before date

We recommend using our material within one year after receipt.

Hot stamping film

- BS range from ITW Foils (ITW group, more information on www.itwfoils.com)
- HC and AS range from Kurz
(More information on www.kurz.de)

Further information

Neutral product (no damage on precious metals), free of azoic substances, free of asbestos
Free of volatile organic compounds,
Lynel Fur SG meets toys standard EN 71 part 3.
Specific chromatic tolerances are applied for each colour.
(Please contact us for more detailed information).

DISTRIBUTED by



SENTIS
CZECH REPUBLIC

Phone: +420.311 612 055
F a x : +420.311 516 535

www.sentis.cz
sentis@sentis.cz

