

Technical Data Sheet

ACURA Mull (MICRA)

Basematerial	100% Cotton laminated on silk paper and Polyethylene		
	Cotton $28 \pm 1 \text{ g / m}^2$	warp	tex 16,5 picks 1 cm 10
		weft	tex 16,5 picks 1 cm 7
	Paper 25 g / m^2	silk paper	
	Glue $13 \pm 2 \text{ g / m}^2$	water - soluble	
	Polyethylene $33 \pm 2 \text{ g / m}^2$	Polyethylene LDPE	

Total Weight	g / m ² 99 $\pm$ 5
---------------------	-------------------------------

Thickness	mm 0,21 $\pm$ 0,01
------------------	--------------------

Tensile Strength	warp	N / 50 mm	>	200
Tensile Strength	weft	N / 50 mm	>	140

Percentage Elongation at break	warp	%	<	5
Percentage Elongation at break	weft	%	<	5

DISTRIBUTED by



SENTIS
CZECH REPUBLIC

Phone: +420.311 612 055

F a x : +420.311 516 535

www.sentis.cz
sentis@sentis.cz