

MIRAGE PESCARA & DISTRESSED

PRODUCT DATA SHEET

CLASSIFICATION	MATERIAL SPECIFICATION
Standard Width	1371mm
Standard Roll Length	100 Mtrs
Standard Roll Weight	29 kgs
Sheets	68x100 cm
Core Size	7.62cm I.D.
Minimum Order Qty	5 Linear Meters
Material Composition	30% - Acrylic Coating 70% - Latex Impregnated Paper 100% Chemical Pulp Lignin and Carbon Free
Recycled Content	15% Recycled / (10% PCW – Black Base Only)
Process of Production	Sulfate
Coating Composition	Pescara : Acrylic Polyurethane Distressed : Acrylic Latex
Average Thickness	.229mm
Average Weight	180gsm
Decorating Applications	Foil Stamp / Blind Stamp / Silkscreen / Thermo
Branding Recommendations	Heat: 135 to 149° C Pressure: 413 to 551 kpa Dwell Time: .5 to 1 Seconds For branding it is recommended to use TEFLON coated stamping die to achieve best results.
Typical Uses	Book Covers, Stitched Diary/Journal Covers, Box & CD Wraps, Slip Cases, Stitched Diary/Journal Covers, Photo Albums, Looseleaf & Lever Arch Files
Recommended Gluing	Back & Face: PVA / Synthetic
Commodity/Harmonized Tariff	Paper:Acrylic Coated, Latex Impregnated: 4811.90.00
Stock Sample Size	68x50 (grain short)
Specials Min. Order Qty	Consult Mill
Information Last Updated	06/21

Above information subject to change without notice.

FSC MIX: RA-COC-003258 100% Solvent-Free

Meets EU Reach, Rohs, CPSIA, EN71, and TSCA Requirements

Due to the nature of burnishing elements contained in the Mirage® coating formulation, mixing lots is not recommended.

DISTRIBUTED by



SENTIS
CZECH REPUBLIC

Phone: +420.311 612 055

F a x : +420.311 516 535

www.sentis.cz

sentis@sentis.cz