

TECHNICAL DATA SHEET

VIRPUL

TECHNICAL SPECIFICATIONS

Tipo di prova (data sheet)	unità (units)	long. (long.)	trasv. (across)	Metodo (test method)
Carico di rottura (Tensile strength)	Kg / 5 cm	40	10	UNI 4818-2.10 satra pm. 29
Allungamento rottura (Ultimate elongation)	%	>20	>100	UNI 4818-2.10 satra pm. 29
Resistenza lacerazione (Tear strength)	Kg	1	0,4	UNI 4818-2.10 satra pm. 30
Adesione (Peel adhesion)	Kg / 2,5 cm	0,8 + 0,1	0,8 + 0,1	UNI prct 263 satra am 10
Resistenza flessioni +20°C (Flexion strength)	n° flex			bally test 90 flex/min.
Resistenza flessioni -5°C (Flexion strength)	n° flex			
Permeabilità vapor acqueo (Water vapor permeability)	ml/mq 24 h.			UNI prct 260
Assorbimento acqua (Water absorption)	ml/mq 15'			UNI prct 258
Aggressione solventi (Solvent resistance)	Solub. Insolub.	Dmf altri solventi (conventional solvents)		UNI prct 262
Abrasione	numero giri			Martindale
	KPa			
Peso (Weight)	gr/mq		230 +- 10	
Spessore (Thickness)	mm		0,60 + 0,05	
Altezza (Width)	cm		139- 140	
Composizione (Composition)	tessuto (textile)	%	22 + 2	
	pu (pu)	%	78 + 2	

DISTRIBUTED by



SENTIS
CZECH REPUBLIC

Phone: +420.311 612 055

F a x : +420.311 516 535

www.sentis.cz
sentis@sentis.cz